

AASHTO Specifications

AASHTO #	4"	3-1/2"	3"	2-1/2"	2"	1-1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16	#50	#100
1	100%	90-100%		25-60%		0-15%		0-5							
2			100%	90-100%	35-70%	0-15%		0-5							
24			100%	90-100%		25-60%		0-10	0-5						
3				100%	90-100%	35-70%	0-15		0-5						
357				100%	95-100%		35-70		10-30%		0-5%				
4					100%	90-100%	20-65%	0-15%		0-5%					
Area #4				100%	90-100%	60-90%	10-30%			0-1%					
467					100%	95-100%		35-70%		10-30%	0-5%				
5						100%	90-100%	20-55%	0-10%	0-5%					
56						100%	90-100%	40-85%	10-40%	0-15%	0-5%				
57						100%	95-100%		25-80%		0-10%	0-5%			
6							100%	90-100%	20-55%	0-15%	0-5%				
67							100%	90-101%		20-55%	0-10%	0-5%			
68							100%	90-102%		30-65%	5-25%	0-10%	0-5%		
7								100%	90-100%	40-70%	0-15%	0-5%			
78								100%	90-100%	40-75%	5-25%	0-10%	0-5%		
8									100%	85-100%	10-30%	0-10%	0-5%		
89									100%	90-100%	20-55%	5-30%	0-10%	0-5%	
9										100%	85-100%	10-40%	0-10%	0-5%	
10										100%	85-100%				10-30%