

Railroad Aggregate Properties

AREA #4A	
Test	Result
Bulk Specific Gravity	2.782
Bulk Specific Gravity (SSD)	2.792
Apparent Specific Gravity	2.81
Absorption	0.36
L.A. Abrasion	20.00%
Sodium Sulfate	1.9% Loss
Voids in Aggregate	41.70%

AREA #57	
Test	Result
Bulk Specific Gravity	2.741
Bulk Specific Gravity (SSD)	2.759
Apparent Specific Gravity	2.791
Absorption	0.66
L.A. Abrasion	19.42%
Sodium Sulfate	0.4% Loss